

| Properties | Unit | TP4208 | TP4407 | TP6603 | TP6802 |
|------------------------------|---------|--------------------------|-----------|-----------------------|-----------|
| 含水量 Moisture content | ppm | < 1000 | < 1000 | < 1000 | < 600 |
| 胺基 Amino end group | meq/kg | 44 ± 3 | 51 ± 3 | 39 ± 3 | 31 ± 3 |
| 可萃取物 Extractable | % Max | < 0.6 | < 0.6 | < 0.6 | < 0.6 |
| 熔點 Melting point | °C | 220 ~ 225 | 220 ~ 225 | 220 ~ 225 | 220 ~ 225 |
| 流動率 Melt flow index | g/10min | 180 ~ 230 | 70 ~ 125 | 30 ~ 60 | 15 ~ 35 |
| 應用範圍 Suitable application | | Compounding Injection | | Compounding Extrusion | |

Packaging: 800 kgs Jumbo Bag <16 mt / 20' Container>
25 kgs Paper Bag <15 mt / 20' Container>

2013